



Bajoriego EIRL
 Bartolome Sharp 1659
 Vitacura - Santiago
 CP 7650329
www.bajoriego.cl

FICHA TECNICA MANGA DE FILTRO PARA SUPER SUCKER

POLYESTER 500gr.

Material		Polyester (PET)
Weight		500 ± 50 g/m²
Thickness (indicative value)		2.00mm
Permeability		150 ± 40 l/dm²/min
Breaking strength	Warp	>100 daN/5cm
Weft		>80 daN/5cm
Breaking elongation (relative value)	Warp	20%
Weft		20%
Finishing		Singed and calendered
Resistance to temperature (Dry)		Continuous 150°C Peak 170°C
Moisture content (65% RAH -20°C)		0.2 -0.5 %
Mass		1.38 g/cm³
Resistance to acid		Average
Resistance to alkali		Poor
Resistance to hydrolysis		Poor
Resistance to solvent		Excellent
Resistance to oxid		Excellent
Special Properties		Thermoplastic fibre with good mechanical resistance in a dry atmosphere up to 15°C